




# US 80NW

## Nonwoven Geotextile



NTPEP APPROVED - GTX-2019-01-292. US 80NW is a nonwoven needlepunched geotextile made of 100% polypropylene staple filaments. US 80NW resists ultraviolet and biological deterioration, rotting, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. US 80NW meets the following M.A.R.V. values except where noted:



PROPERTY	TEST METHOD	ENGLISH	METRIC
Weight <span style="border: 1px solid black; border-radius: 10px; padding: 2px;">Typical</span>	<a href="#">ASTM D-5261</a>	3.1 oz/y <sup>2</sup>	105.09 g/m <sup>2</sup>
Grab Tensile Strength	<a href="#">ASTM D-4632</a>	80 lbs	356 N
Elongation @ Break	<a href="#">ASTM D-4632</a>	50 %	50 %
Mullen Burst <sup>(3)</sup>	<a href="#">ASTM D-3786</a>	145 psi	1,000 kPa
Pin Puncture <sup>(3)</sup>	<a href="#">ASTM D-4833</a>	40 lbs	178 N
CBR Puncture	<a href="#">ASTM D-6241</a>	175 lbs	779 N
Trapezoidal Tear	<a href="#">ASTM D-4533</a>	30 lbs	134 N
Apparent Opening Size <sup>(1,2)</sup>	<a href="#">ASTM D-4751</a>	50 US Sieve	0.297 mm
Permittivity <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	2.2 Sec <sup>-1</sup>	2.2 Sec <sup>-1</sup>
Water Flow Rate <sup>(1)</sup>	<a href="#">ASTM D-4491</a>	150 g/min/f <sup>2</sup>	6,112 L/min/m <sup>2</sup>
UV Resistance @ 500 Hours	<a href="#">ASTM D-4355</a>	70 %	70 %

<sup>(1)</sup> At the time of manufacturing. Handling, storage, and shipping may change these properties.

<sup>(2)</sup> Maximum average roll value (MaxARV).

<sup>(3)</sup> Historical reference values. These properties are no longer recognized by ASTM or AASHTO for geosynthetics.

## US 80NW Shipping & Packaging Information

SIZE	DIAMETER	WIDTH	WEIGHT	AREA	ROLLS PER TRAILER
12.5' x 360'	12"	12.5'	145 lbs	500 y <sup>2</sup>	260
15' x 360'	12"	15'	165 lbs	600 y <sup>2</sup>	210

**US Fabrics, Inc. | 3904 Virginia Avenue | Cincinnati, OH 45227**  
**Phone: (800) 518-2290 | Fax: (513) 217-4420 | email: [info@usfabrics.com](mailto:info@usfabrics.com)**

This information is provided for reference only and is not intended as a warranty or guarantee.  
 US Fabrics assumes no liability in connection with the use of this information.