
TRIMITEC UNDERLAY





PHYSICAL PROPERTIES

Dimensions

1220 mm x 915 mm x 5.5 mm

Tolerances (Ex mill)

Length \pm 1.0 mm Width \pm 1.0 mm Thickness \pm 0.15 mm

Squareness

Variation in diagonals not more than

1.0 mm

Area

1.12 m²

Packaging

Bulk packs of (120 sheets)

Physical properties

Density 960 kg/m³
Mass/unit area 5.3 kg/m²
Modulus of rupture 30 MPa
Modulus of elasticity 4000 MPa
Impact strength 4000J/m²
Internal bond strength 1000 kPa
Thermal conductivity 0.11 W/mK

Hygro-expansivity 0.25% change in

face dimensions over 50% - 90% RH

PREPARATION

Adequate underfloor ventilation is essential to prevent distortion, possible decay and excessive movement of the subfloor, frame support, underlay and overlay. If inadequate ventilation exists, subsequent damage to the floor covering material or adhesive system will occur. This is especially important where impervious final floor coverings are used as these prevent the escape of moisture through the floors.

The moisture content of timber, plywood or particleboard subfloors and their structural supports must be checked before the underlay is installed. Acceptable moisture content range is 9% -14%. Where existing timber, plywood or particleboard floors are to be used as a sub-floor for hard underlay installation, any worn, rough, cupped or warped surfaces must be repaired. Imperfections such as hollows, cracks and uneven joints will affect the quality of the finished floor. The sub floor must be sanded, filled or replaced to achieve a plane, smooth surface prior to the installation of the underlay. The sub-floor must retain its structural adequacy.

CONDITIONING

Trimtec Underlay must be conditioned to allow it to reach equilibrium with its surroundings before being fixed to the sub-floor. The most prominent cause of joint show through is failure to properly condition underlay. To condition Trimtec Underlay each individual sheet must be exposed to air circulation in the environment for which it is to be installed for at least 24 hours before being fixed.

Keep clear of sharp protrusions. Stack panels flat on pallets or timber runners in a dry area with moderate temperature and reasonably constant relative humidity. Storage in direct sunlight, damp locations or hot, dry buildings should be avoided.

Trimtec Underlay must not be conditioned or fixed when extreme weather conditions (such as relative humilities of less than 25% or greater than 90%) are temporarily experienced. In these situations conditioning and fixing must be delayed until normal weather conditions return.

LAYOUT

Trimtec Underlay is designed to be installed smooth side up. Starting on a straight wall with the long edges of the underlay perpendicular to the sub floor joins. Trimtec Underlay is to be laid using a brick pattern as shown in the diagram.

It is crucial to the performance of the product that the following are provided to allow room for expansion:

- 3 mm gap around the perimeter of the wall
- 0.4 mm gap between sheets

CUTTING

Trimtec Underlay can be cut using the following tools:

- Utility knife (heavy duty blade not break away type). Using a utility knife is the easiest method of cutting Trimtec Underlay. Simply score the surface of the underlay where the cut is required and snap the underlay. It will break cleanly at the score.
- Circular saw (33 mm tooth)
- Jig saw (fine tooth) or timber blade
- Hand saw (fine tooth) or panel saw

ADHESIVES

ADHESIVES FOR TIMBER SUB-FLOORS

In addition to mechanical fixings, adhesives must be used when Trimtec Underlay is fixed to plywood, particleboard or pine sub-floor. The following adhesives are suitable:

- Polymer 1017 Polyurethane Adhesive or
- Polymer 1018 Fast Setting Polyurethane Adhesive or
- GS500 Polyurethane Adhesive


ADHESIVES FOR CONCRETE SUB-FLOORS

- Polymer 1017 Polyurethane Adhesive or
- Polymer 1018 Fast Setting Polyurethane Adhesive or
- GS500 Polyurethane Adhesive

In case of structural movement or excessive changes in atmospheric relative humidity in a building, the filling of expansion joints in Trimtec Underlay is not recommended.

Avoid alkaline substances, as high pH values can promote swelling in natural reconstituted timber products.






FASTENER SPACING

The correct spacing between fixings when installing Trimtec Underlay to timber subfloors is shown in the Fixings diagram.

Fixings must be provided:

- 10mm in from the perimeter of the sheet
- 75mm around the perimeter of the sheet
- 150mm through the body of the sheet

Avoid nailing into sub-floor joints. Slightly overdrive all fixings to provide a smooth finish product. Ensure that all fixings are 0.4mm (business card or Stanley knife width) below the surface of the Trimtec Underlay.



FIXINGS

FIXING TO A PLYWOOD OR PARTICLEBOARD FLOOR

The following fixings are recommended for installing Trimtec Underlay over plywood or particleboard sub-floors. Fixings must be used in conjunction with an appropriate adhesive (refer to Adhesives manufacturer for further recommendations). **25mm x 2.5mm head ring grooved buttress type underlay nails**.

FIXING TO A TIMBER SUB-FLOOR

The following fixings are recommended for installing Trimtec Underlay over solid timber flooring.

Staples: 22mm resin coated staples or staples 3mm longer than the existing sub-floor.

FIXING TO A CONCRETE SUB-FLOOR

Ensure the concrete is dry and clean. Dry lay the underlay allowing the recommended expansion of 0.4mm between sheets and 3mm around the perimeter.

Prepare the concrete sub-floor as per the adhesive manufacturer's recommendations. Remove the tiles of Trimtec Underlay and apply adhesive to sub-floor in accordance with the adhesive manufacturers recommendations. Place the Trimtec Underlay sheets into the adhesive and roll with a 40 kg roller weight. Allow the adhesive to cure for the recommended period.

Additional weight may be required if changes in relative humidity delays adhesive bond time or cause the underlay to lift around the perimeter.

FINISHING

Using a flat based sanding machine or sanding block, carefully sand the underlay joins to a level plane. Lightly sand the fixing points to remove any loose fibre.

Sweep or vacuum the floor so that all dust and loose fibre is removed prior to installing the floor covering in accordance with the manufacturers recommendations.



PH: 1800 040 080 Aussie Made, Aussie Laid